

Datasheet: parHeat 68

Updated: 01-03-18

Produced by: Smurfit Kappa Parenco B.V.

Basic properties		Test Method	(nominal values)		
Grammage	(EN ISO 536)	g/m ²	45	48,8	52
Structural properties		(nominal values)			
Thickness	(EN ISO 534)	µm	48	52	56
Density	(EN ISO 534)	kg/m ³	935	935	930
Bulk	(EN ISO 534)	cm ³ /g	1,07	1,07	1,08
Roughness (Bendtsen 98 kPa)	(ISO 8791-2)	ml/min	60	60	60
Optical properties		(nominal values)			
Brightness, ISO	(ISO 2470 -2)	%	68	68	68
Opacity	(ISO 2471)	%	90	91	92
L*	(ISO 5631-2)		86,5	86,5	86,5
a*	(ISO 5631-2)		-1,0	-1,0	-1,0
b*	(ISO 5631-2)		4,0	4,0	4,0
Printing method		Heatset			

All papers produced by Parenco are based on 100% recycled paper.



FSC recycled

Parenco holds the FSC Chain of Custody certificate No. DNV-COC-000643, issued by DNV Norway

Parenco is ISO 14001:2004 certified